

The Impact of Residual Stresses on a Wire-Cut Edm Cutting Process

ABSTRACT:

Wire cut EDM is an exceptionally complex method that is used in precision manufacturing. Due to the minute residual stresses that exist inside a grain, generally as an outcome of the presence of disengagements and other glasslike surrenders, lingering stresses delivered during cutting tasks should be thought about. The essential objective of this examination is to give an outline of flow improvements in the field of leftover pressure age and their impact on various factors like surface unpleasantness, dielectric material used, and heartbeat on schedule during wire cut EDM. Analyze the strategies for estimating lingering pressure momentarily also.

Keywords: Wire-Cut EDM, Residual Stresses, Performance Parameter, Advance Manufacturing Process.

I. INTRODUCTION

For precise component production, the WEDM is well known cutting technique. Wire electrical discharge is used in the nuclear reactor and automobile industries to manufacture complex, high-precision components. The WEDM method uses a pulsating current to erode material at the work piece and tool. At the conclusion of the discharge cycle, part of the molten metal solidifies again and is deposited on the cutting surface.

The tensions that remain in a material or body after manufacturing and processing are referred to as residual stresses. Techniques for measuring residual stress measure strains rather than stresses. The residuals are then calculated using material characteristics like Young's modulus, Poisson's ratio, and Young's ratio.

II. LITERATURE SURVEY

J. Crookall et al. [1] at the University of California, San Diego discovered that electro-discharge machining induces extremely high residual tensile stresses. Residual stresses in various materials are proportional to their thermal and other characteristics and are usually unaffected by the tool electrode and dielectric material. They were found using the bending-deflection method, which is a very sensitive approach for constantly monitoring deflections caused by electrochemical cell stresses.

J. Liu et al. [2] simulate residual stress generation in die-sinking EDM of the ASP 23 tool steel, a novel modelling technique accounting for large random discharges has been devised. The highest value of average residual stress is determined in the subsurface rather than at the top surface, which is consistent with experimental results. The low residual stress on the surface is a result of the roughness of the surface.

B. Ekmekci et al. [3] investigates in their study that high tensile residual stresses are seen to increase quickly with depth, reaching a maximum value around the yield strength, and then rapidly decaying to compressive residual stresses in the material's core. This pattern is independent on the thermal characteristics of the work piece material and the dielectric liquid. Additionally, there is a strong relationship between the hardness depth and the afflicted layers.

R. Pan et al. [4] observed in their research that residual stresses are often generated during the quenching of aluminium alloys and pose a danger of cracking or distorting during following production operations. It is critical to investigate ways for minimising the RS in quenched components. Cold rolling (CR) was used in this study to remove the RS from quenched AA7050 blocks. Although CR converts near-surface residual stresses from high compression to high tension in the rolling direction, it achieves exceptional RS alleviation in the core.

B. Ekmekci et al. [5] in their research work concludes that the dielectric liquid and electrode type have been investigated with the impact of retention of austenite and residual strains using X-ray diffraction methods on the structure of the white layer in electric discharge machining surfaces. The current study indicates that when machining with kerosene dielectric liquid, the surface is saturated with carbon regardless of the tool electrode

material. However, residual Austenite forms on the surface as a result of carbon absorption from the graphite tool electrode when using de-ionized water dielectrics.

H.-T. Lee et al. [6] perform the study to determine the effect of the EDM parameters on different elements of the surface integrity of AISI 1045 carbon Steel, this research carried out small area electro-discharging (EDM), using a low wear-rate copper/tungsten electrode in the diameter of 1.5 mm. The findings show that visible fractures in larger white layers are always apparent. It is observed that the MRR, SR and surface fracture density diminish during a prolonged period of the pulse.

S. Bhattacharya et al. [7] introduce the FE method that has been applied to simulate residual stresses generated during WEDM cutting on the HAZ of P91 steel. Residual stresses are of Tensile in nature and can affect the service life of the components subjected to fatigue loading. This paper also describes the size of craters and heat affected zone.

W.P. Rehbach et al. [8] perform the study and develop an EDM drilling process for measuring residual stress in high-performance materials whose stress state is difficult to obtain using a commonly used technology called high-speed (HS) hole-drilling (ASTM Standard E837). SKD11 (JIS) tool steels were prepared at various pre-stress levels to simulate any residual stress that may exist in the work pieces. The experimental results indicate that the stress measurement curves for both EDM conditions are parallel to the ideal curve. This demonstrates the feasibility of measuring residual stress on materials with a high degree of hardness and wear resistance.

K. Bonny et al. [9] discovered that wire-EDM produces more friction and wear than grinding and polishing. This trend was confirmed by X-ray diffraction measurements, which revealed residual tensile surface stresses in WC following wire-EDM, in contrast to compressive surface stresses following ground and polished equivalents. Additionally, the researchers discovered that reduced surface quality had a significant effect on (running-in) wear behaviour, including binder depletion, residual surface stress, thermal grain cracking, and increased surface roughness.

Bulent Ekmekcia et al. [10] on the surfaces of electric discharge machined components, significant residual tensions occur. They rise in value as they approach the surface and eventually achieve their maximum worth. This highest value is close to the material's ultimate tensile strength. The layer removal approach is utilised in this work to determine the residual stress profile generated by die sinking type EDM as a function of depth under the surface. On samples machined with extended pulse durations, cracking and its effects are also investigated.

Philips Analytical et al. [11] the author describes the process of creating and configuring an electronic database for elastic constants. For materials having cubic, hexagonal, or tetragonal crystal symmetry, calculation models such as Voigt, Reuss, and Hill are provided. Data entries are checked to avoid the introduction of new typing mistakes.

Hwa-Teng Lee et al. [12] the measurement of residual stress in AISI D2 cold work tool steel is investigated using the electro discharge machining (EDM) hole-drilling technique. The microstructure and hardness of the white layer that had re-solidified on the EDMed surface were studied using scanning electron microscopy, transmission electron microscope, and Nano indentation methods.

Shuvra Das et al. [13] in this paper, a finite element-based model of the electric discharge machining (EDM) process is introduced. The transitory temperature distribution, liquid-to-solid-state material transition, residual stress, and ultimate crater shape are all predicted by the model. In the near future, the model will be extended to mimic the impacts of numerous pulses.

Y.H. Guua et al. [14] AISI D2 tool steel was used for the investigation of electrical discharge machining (EDM). A study was conducted to determine the surface characteristics and machining damage produced by EDM in terms of machining parameters. The results show that the thickness of the recast layer and the roughness of the surface are related to the amount of power used. Increased peak currents result in an increase in the melting of the material, resulting in significant damage to the surface and subsurface areas of the structure.

F. Ghanem et al. [15] This research looks at how machining affects the fatigue life of an EN X155CrMoV12 tool steel (SAEJ438b) The cutting processes of electro-discharge machining (EDM), which has a high energy

density, and milling, which is more traditional, were compared. When comparing the EDM samples to the milled samples, it was discovered that the fatigue limit was reduced by about 35%. This was ascribed to the presence of a tensile residual stress state after EDM, which was coupled with substantial phase change and hydrogen embrittlement to produce the observed results. Compressive residual stresses were found in the milled surfaces, despite the fact that there was no microstructural change or surface cracking.

J.F. Liu et al [16] the current EDM modelling approaches are only capable of simulating one discharge. In die-sinking EDM of the ASP 23 tool steel, a novel model has been created to predict residual stress generation. The highest value of average residual stress is found in the subsurface rather than the top surface, which is consistent with experimental results. To produce reduced tensile residual stress, lower discharge energy is desired in EDM.

A. Umaphathi et al.[17] Using synchrotron radiation X-rays from BL-11 at INDUS-2, RRCAT, Indore, India, the residual stress distribution due to laser peening without coating (LPwC) was studied. The findings demonstrate that depending on the titanium alloy, LPwC causes greater and deeper residual stress. Although compressive residual stress (CRS) was found in the majority of instances, tensile residual stress (TRS) was only found in a handful of them.

N.S. Rossini et al. [18] many constructed structures and components have residual stresses. For different types of components, several methods for measuring residual stress have been devised. The purpose of this study is to identify the various residual stress measuring methods and to give an overview of some of the most recent advancements in this field. The breadth, physical limitations, advantages, and drawbacks of each approach are outlined. Finally, it suggests some possible future development directions.

X. Yanga et al. [19] the generation mechanism of residual stress and its distribution were simulated using molecular dynamics techniques in this research. Residual stress is one of the key features of the surface machined by electrical discharge machining (EDM). It was discovered that during discharge, a greater pressure gradient was formed in the melting area. This indicates that cracks can easily form in the re-solidified layer.

Yukio Ueda et al. [20] in a new article, a new method for measuring three-dimensional residual stresses is provided. The approach is used to calculate residual stresses in a quenched shaft, and it is shown to be reliable and practical. It is based on Sachs' finite element approach, which he developed in 1975.

Philip Allen et al. [21] in many materials, micro electro-discharge machining (micro-EDM) is an excellent method for achieving burr-free machined micron-size holes. A thermo-numerical model that replicates a single spark discharge process is used to investigate material removal. The impacts of critical EDM parameters like pulse length on the crater dimension and tool wear % are investigated using the numerical model. The model predicts that when the pulse rate increases, the percentage of tool wear falls, with molybdenum having a considerably greater percentage of tool wear than steel under machining circumstances.

III. CONCLUSION

The following are the findings based on various literature reviews.

- Residual stresses in different materials are related to their thermal and other properties, and they are generally unaffected by the tool electrode and dielectric material.
- Between the hardness depth and the number of affected layers, there is a significant connection.
- The subsurface, rather than the top surface, has the greatest average residual stress value. In EDM, decreased discharge energy is sought to minimise tensile residual stress.
- It was found that a larger pressure gradient was generated in the melting region during discharge. This implies that fractures in the re-solidified layer are likely to develop.
- Increased pulse rate results in a decrease in the percentage of tool wear.
- The material removal rate, surface roughness, and surface fracture density all decrease with the duration of the pulse.

REFERENCES

- [1] J. Crookall, B. Khor, Residual stresses and surface effects in electro-discharge machining, in: Proceedings of the Thirteenth International Machine Tool Design and Research Conference, Springer, 1973, pp. 331-338.
- [2] J. Liu, Y. Guo, Residual stress modeling in electric discharge machining (EDM) by incorporating massive random discharges, *Procedia Cirp*, 45 (2016) 299-302.
- [3] B. Ekmekci, O. Elkoca, A. Erman Tekkaya, A. Erden, Residual stress state and hardness depth in electric discharge machining: de-ionized water as dielectric liquid, *Machine science and technology*, 9 (2005) 39-61.
- [4] R. Pan, T. Pirling, J. Zheng, J. Lin, C.M. Davies, Quantification of thermal residual stresses relaxation in AA7xxx aluminium alloy

- through cold rolling, *Journal of Materials Processing Technology*, 264 (2019) 454-468.
- [5] B. Ekmekci, Residual stresses and white layer in electric discharge machining (EDM), *Applied surface science*, 253 (2007) 9234-9240.
- [6] H.-T. Lee, F.-C. Hsu, T.-Y. Tai, Study of surface integrity using the small area EDM process with a copper-tungsten electrode, *Materials Science and Engineering: A*, 364 (2004) 346-356.
- [7] S. Bhattacharya, A. Mishra, T. Singh, S. Bandyopadhyay, S. Kumar, G. Dey, V. Kain, Simulation of residual stress using thermomechanical analysis on wire EDM cut surface, *Materials Today: Proceedings*, 19 (2019) 462-467.
- [8] H.-T. Lee, W.P. Rehbach, F.-C. Hsu, T.-Y. Tai, E. Hsu, The study of EDM hole-drilling method for measuring residual stress in SKD11 tool steel, *Journal of materials processing Technology*, 149 (2004) 88-93.
- [9] K. Bonny, P. De Baets, J. Quintelier, J. Vleugels, D. Jiang, O. Van der Biest, B. Lauwers, W. Liu, Surface finishing: Impact on tribological characteristics of WC-Co hardmetals, *Tribology International*, 43 (2010) 40-54.
- [10] B. Ekmekci, A.E. Tekkaya, A. Erden, A semi-empirical approach for residual stresses in electric discharge machining (EDM), *International Journal of Machine Tools and Manufacture*, 46 (2006) 858-868.
- [11] A. Vermeulen, An elastic constants database and XEC calculator for use in XRD Residual stress analysis, *Advances of X-ray Analysis*, 44 (2001) 128-133.
- [12] H.-T. Lee, J. Mayer, F.-C. Hsu, W.P. Rehbach, T. Weirich, A. Dimiyati, T.-Y. Tai, Application of EDM hole-drilling method to the measurement of residual stress in tool and Carbon steels, (2006).
- [13] S. Das, M. Klotz, F. Klocke, EDM simulation: finite element-based calculation of Deformation, microstructure and residual stresses, *Journal of materials processing technology*, 142 (2003) 434-451.
- [14] Y. Guu, H. Hocheng, C. Chou, C. Deng, Effect of electrical discharge machining on surface characteristics and machining damage of AISI D2 tool steel, *Materials Science and Engineering: A*, 358 (2003) 37-43.
- [15] F. Ghanem, H. Sidhom, C. Braham, M.E. Fitzpatrick, Effect of near-surface residual stress and microstructure modification from machining on the fatigue endurance of a tool steel, *Journal of materials engineering and performance*, 11 (2002) 631-639.
- [16] J. Liu, Y. Guo, Residual stress modeling in electric discharge machining (EDM) by incorporating massive random discharges, *Procedia Cirp*, 45 (2016) 299-302.
- [17] A. Umaphathi, S. Swaroop, Measurement of residual stresses in titanium alloys using synchrotron radiation, *Measurement*, 140 (2019) 518-525.
- [18] N. Rossini, M. Dassisti, K. Benyounis, A.-G. Olabi, Methods of measuring residual stresses in components, *Materials & Design*, 35 (2012) 572-588.
- [19] J. Liu, Y. Guo, Modeling of white layer formation in electric discharge machining (EDM) by incorporating massive random discharge characteristics, *Procedia CIRP*, 42 (2016) 697-702.
- [20] X. Yang, X. Han, F. Zhou, M. Kunieda, Molecular dynamics simulation of residual stress generated in EDM, *Procedia CIRP*, 6 (2013) 432-437.
- [21] Y. Ueda, K. Fukuda, Y.C. Kim, New measuring method of axisymmetric three-dimensional residual stresses using inherent strains as parameters, (1986).